

Amend **Section 608 - Sidewalks** to read as follows:

"SECTION 608 - SIDEWALKS

608.01 Description. This work includes constructing concrete sidewalks according to the contract.

608.02 Materials. Materials shall conform to the following:

Bed Course Material for Sidewalks and Curbing 703.16(A)

Joint Fillers 705.01

Reinforcing Steel 709.01

Concrete for sidewalks shall conform to Section 601 - Structural Concrete and shall be Class B.

Concrete mixes will be subject to inspection and tests at the mixing plants for compliance with quality requirements.

The condition of materials will be subject to inspection for acceptance before or during incorporation of materials into the work.

608.03 Construction Requirements

Place concrete sidewalks four inches thick either reinforced or unreinforced as shown in the contract.

(1) Preparation. Shape and compact the foundation to a firm even surface conforming to the section shown in the contract. Remove and replace soft and yielding materials with acceptable material.

(2) Forms. Forms shall be of wood or metal and shall extend for the full depth of the concrete. Forms shall be straight, free from warp and of sufficient strength to resist the pressure of the concrete without springing. Bracing and staking of forms shall be such that the forms remain in both horizontal and vertical alignment until their removal.

(3) Placing Concrete. Moisten the foundation thoroughly

immediately before placing the concrete. Place the concrete according to Section 503 - Concrete Structures.

(4) Finishing. Work the surface with a wooden float and broom finished. The Engineer will not permit plastering of the surface.

Edge the outside edges of the slab and joints with a 0.25 inch radius edging tool.

The surface of the sidewalk shall be a true plane with a 0.25 to 12 slope toward the roadway.

(5) Joints. Form the construction joints around appurtenances such as manholes and utility poles extending into and through the sidewalk. Install 0.25-inch thick premolded expansion joint filler in these joints. Install 0.5-inch thick premolded expansion joint fillers between concrete sidewalks and any fixed structure such as a building or bridge. Extend the expansion joint material from the bottom of the slab to approximately 0.25 inch below the top surface of the concrete construction.

Divide the slab between expansion or construction joints into sections approximately five feet in length by transverse weakened plane joints formed by a jointing tool. Also, provide transverse weakened plane joints when the time period between consecutive concrete placements is more than 45 minutes. Form the weakened plane joints into the concrete to a depth of 0.25 of the thickness and approximately 0.125 inch in width with a scoring tool which will leave the edges round. Where slabs are more than 7 feet in width, form weakened plane joints longitudinally to obtain secure uniform blocks that are approximately square. Install weakened plane joints where the corners of drop inlets project into the sidewalk.

Match joints with the curb or pavement joints.

(6) Curing. Cure the concrete for at least 72 hours. Curing shall be by moist burlap or mats or by other accepted methods. During the curing period, exclude pedestrian and vehicular traffic. Exclude the vehicular traffic for such additional time as the Engineer may specify.

608.04 Method of Measurement. The Engineer will measure concrete sidewalk per square yard complete in place.

608.05 Basis of Payment. The Engineer will pay for the accepted concrete sidewalk at the contract unit price per square yard complete in place. The price shall be full compensation for excavating; backfilling; installing reinforcing steel; placing and compacting bed course material; furnishing and placing the concrete; installing expansion joint material, weakened plane joint, and ramps; and furnishing labor, materials, equipment, tools, and other incidentals necessary to complete the work.

The Engineer will make payment under:

Pay Item	Pay Unit
Concrete Sidewalk	Square Yard"

END OF SECTION