

SECTION 712 - MISCELLANEOUS

Make the following Subsection a part of said Section:

Amend 712.57 **Hot Applied Rubberized Sealant** by revising the table to read as follows:

TESTS	SPECIFICATIONS LIMITS
Brookfield Viscosity at 400 °F. (ASTM D 3236)	75 poise maximum
Penetration, 125 °F., 50g. 5 seconds (ASTM D 5)	50 maximum
Penetration, 77 °F., 100g. 5 seconds (ASTM D 5)	10 - 25
Softening Point (ASTM D 36)	210 °F.
Ductility, 77 °F. (ASTM D 113)	15 cm minimum
Flexibility, 0 °F. Crafcro Procedure	Pass
Recommended Pour Temperature	380 °F.
Safe Heating Temperature	420 °F.
Specific Gravity at 60 °F. (material purity)	1.05 maximum"

END OF SECTION