

1 Amend **Section 401 - Asphalt Concrete Pavement** to read as follows:

2
3 **"SECTION 401 - ASPHALT CONCRETE PAVEMENT**

4
5 **401.01 Description.** This section applies to the construction of asphalt
6 concrete pavement on a prepared surface according to the contract.

7
8 Include pavement wearing course mixture and a binder course mixture
9 when specified herein.

10
11 **401.02 Materials.** The plant mixed asphalt concrete includes a mixture of
12 aggregate, filler or blending sand, if acceptable, and asphalt cement. Size,
13 uniformly grade, and combine aggregates so that the resulting mixture meets the
14 grading requirements of the job-mix formula. Conform to the following:

15

16 Asphalt Cement	702.01
17	
18 Emulsified Asphalt	702.04
19	
20 Aggregate for Hot Plant Mix Bituminous Pavement	703.09
21	
22 Filler	703.15
23	
24 Blending Sand	703.22
25	
26 Hydrated Lime	712.03

27
28 Asphalt cement shall be PG 64-16.

29
30 **401.03 Job-Mix Formula and Tests.**

31
32 **(A) Job-Mix Formula.** Submit for acceptance, a job-mix formula for
33 each mixture to be supplied for this project. The job-mix formula shall
34 show the grade of cement in the mixture. Furnish only one grade of
35 asphalt cement for the project. The Engineer may change the grade of
36 the asphalt cement one step at no change in unit price. Make grade
37 change only upon written acceptance by the Engineer. Submit a
38 Certificate of Compliance, with substantiating test data, before using each
39 lot or batch of asphalt cement. The Engineer will not accept the asphalt
40 cement without adequate documentation.

41
42 The job-mix formula with allowable tolerances shall be within the
43 master range for the type of asphalt concrete. The job-mix formula for a
44 mixture shall be in effect until modified by the Engineer. Submit for
45 acceptance a new job-mix formula before using the new material.

The job-mix formula for each mixture shall establish:

- (1) a percent of aggregate passing each required sieve size,
- (2) a percent of asphalt cement added to the aggregate, and
- (3) a temperature the mixture is delivered to the point of discharge.

The job-mix formula of the mixture furnished shall be within tolerances in Table 401-I:

TABLE 401-I - RANGE OF TOLERANCES FOR JOB-MIX FORMULA		
Passing No 4 and larger sieves (%)		± 7
Passing No. 8 to No. 100 sieves (inclusive) (%)		± 4
Passing No. 200 sieve (%)		± 2
Bitumen (%)		± 0.4
Temperature of mixture (° F)		± 20

When changing the source of material, establish a new job-mix formula before using the new material. When the results or conditions are unsatisfactory, the Engineer will require the Contractor to establish a new job-mix formula.

The Engineer may allow use of a nominal quantity of blending sand not exceeding 5 percent of the total weight of aggregate.

The Engineer may allow the use of filler material to correct deficiencies in materials passing the No. 200 sieve. Filler added shall not exceed 3 percent by weight of the fine aggregates.

Table 401-II - Limits of Bituminous Binder Content specifies the limits for each type of mixture. In case of dispute as to the optimum asphalt content, discontinue plant operations and allow the Engineer sufficient time to do the necessary laboratory testing. The Contractor may exceed the bituminous binder limits for porous aggregate only if acceptable in writing by the Engineer.

TABLE 401-II - LIMITS OF BITUMINOUS BINDER CONTENT					
MIX NO.	I	II	IV	V	VI
Used For	Binder Course	Binder or Surface Course	Surface Course	Surface Course	County Surface Course (Extra Fine)
Compacted Thickness Individual Layers (Inches)	1.5 to 3	1.25 to 3	1.25 to 3	0.75 to 3.0	1 to 2.5
Bituminous Binder Content Limits (% of dry weight of total aggregate)	4.0 - 6.5	4.5 - 6.5	4.5 - 6.6	5.0 - 7.5	6.0 - 8.0

(B) **Tests.** Base asphalt concrete job-mix formula on tests according to AASHTO T 245 (ASTM D 1559) or AASHTO T 246 (ASTM D 1560). The mixture shall conform to Table 401-IIIA - Job Mix Formula Design Criteria and Table 401 IIIB - Minimum Percent Voids in Mineral Aggregates. Submit the test data used to develop the job mix formula.

TABLE 401-IIIA - JOB-MIX FORMULA DESIGN CRITERIA	
HVEEM Method Mix Criteria	Binder and Surface Course
Stability, minimum	37
Swell, maximum (inch)	0.030
Air voids (%)	3 - 5
Marshall Method Mix Criteria	Binder and Surface Course
Compaction, Number of Blows each end of specimen	75
Stability, minimum (pounds)	1,800
Flow, 0.01 inch	8 - 16
Air voids (%)	3 - 5

TABLE 401-IIIB - MINIMUM PERCENT VOIDS IN MINERAL AGGREGATES					
Nominal Maximum Particle Size, (Inches)	1.5	1.0	0.75	0.50	0.375
VMA, (%)					
HVEEM Method	11	12	13	14	15
VMA, (%)					
Marshall Method	12	13	14	15	16

401.04 Bituminous Mixing Plant Requirements and Process.

(A) Plant Operation.

92 (1) **Preparation of Asphalt Cement.** Heat the asphalt cement
93 to the specified temperature to avoid local overheating. Provide a
94 continuous supply of the asphalt cement to the mixer at a uniform
95 temperature.
96

97 (2) **Preparation of Aggregate.** Dry and heat the aggregate for
98 the mixture to the required temperature. Do not exceed 320
99 degrees F. Properly adjust the flames used for drying and heating
100 to avoid damage to the aggregate and soot on the aggregate. The
101 aggregate, when dried, shall not contain more than 1 percent
102 moisture by weight.
103

104 Immediately after heating and drying, screen the aggregates
105 for batch plants into three or more fractions as specified. Convey
106 the aggregates into separate compartments ready for batching and
107 mixing with asphalt cement.
108

109 (3) **Mixing.** Combine the dried aggregates in the mixer in the
110 quantity of each fraction of aggregates required to meet the job-mix
111 formula. Measure or gage and introduce the asphalt cement into
112 the mixer in the quantity specified by the job-mix formula.
113

114 After introducing the required quantities of aggregate and
115 asphalt cement into the mixer, mix the materials until a complete
116 and uniform coating of the particles and a thorough distribution of
117 the asphalt cement throughout the aggregate is secured. The
118 Engineer will determine wet mixing time for each plant and for each
119 type of aggregate used.
120

121 For hot mix bituminous pavement, produce the mixture at
122 the lowest temperature for a workable mix; however, do not exceed
123 325 degrees F. Introduce the asphalt cement and aggregate into
124 the mixer within 25 degrees F. of each other's temperature.
125

126 (B) **Storage of Aggregates.** Provide sufficient storage space for each
127 size aggregate. Keep the different aggregate sizes separated until the
128 aggregate is delivered to the system feeding the drier. Maintain the
129 storage yard neatly and orderly. The separate stockpiles shall be readily
130 accessible for sampling.
131

132 (C) **General Requirements for Mixing Plants.** Mixing plants shall be
133 capable of handling the proposed bituminous construction.
134

135 (1) **Scales.** The scale requirements shall apply only where
136 proportioning by weight is used;
137

138 (a) **Plant Scales.** Plant scales shall be accurate to 0.5
139 percent throughout the range to be weighed by the
140 Contractor. The poises shall be locked in positions to
141 prevent unauthorized change of position. Instead of plant
142 and truck scales, an acceptable automatic printer system
143 may be provided that prints the weights of the material
144 delivered. Use a system with an acceptable automatic
145 batching and mixing control system. Show evidence of such
146 weights by a weight ticket for each load.
147

148 Measurement Standards Division of the State
149 Department of Agriculture or its authorized representatives
150 will inspect and seal the scale as often as the Engineer may
151 deem necessary to assure their continued accuracy. Have
152 not less than ten 50 pound weights for testing the scales.
153

154 (b) **Truck Scales.** Weigh the bituminous mixture on
155 acceptable scales furnished by the Contractor or on public
156 scales at no cost to the State. The Measurement Standards
157 Division of the State Department of Agriculture or its
158 authorized representatives shall inspect and seal such
159 scales as often as the Engineer deems necessary.
160

161 (2) **Equipment for Preparation of Asphalt Cement.** The
162 storage tanks for the asphalt cement shall be equipped to heat and
163 hold the material at the required temperature. The tanks shall be
164 heated by steam coils or electricity so no flame is in contact with
165 the tank. The circulating system for the asphalt cement shall
166 assure proper and continuous circulation during the operating
167 period.
168

169 Equip storage tanks with provisions for measuring and
170 sampling of material. Calibrate the asphalt storage tanks to an
171 accuracy of 2 percent of the actual amount stored its storage
172 capacity. The storage tank shall be accessible for measuring.
173 Install a sampling outlet including a valve in the bitumen feed lines
174 connecting the plant storage tanks to the bitumen weighing system
175 or spray bar, so samples from the line may be withdrawn slowly
176 during plant operation. Install the sampling outlet between the
177 pump and the return line discharge in such a location that the
178 sampling outlet is readily accessible and free from obstruction.
179 Provide a drainage receptacle for flushing the outlet before
180 sampling.
181

182 (3) **Feeder for Drier.** Provide an accurate mechanical means
183 for uniformly feeding the aggregate into the drier so a uniform
184 production and uniform temperature can be obtained.
185

186 (4) **Drier.** Include driers that continuously agitate the aggregate
187 during the heating and drying process.
188

189 (5) **Screens.** Provide plant screens, capable of screening
190 aggregates to the specified sizes and proportions and having
191 normal capacities greater than the full capacity of the mixer.
192

193 (6) **Bins.** Storage bins shall be divided into at least three
194 compartments to provide separate storage of appropriate fractions
195 of the aggregate. Provide each bin with overflow pipes, of such
196 sizes and at such locations to prevent material from backing up into
197 other compartments or bins. Provide each compartment with an
198 individual outlet gate. The outlet gate shall not leak when closed.
199 The gates shall cut off quickly and completely. The bins shall have
200 means to sample the aggregates.
201

202 (7) **Bituminous Control Unit.** Provide satisfactory means,
203 either by weighing or metering, to obtain the proper quantity of
204 asphalt cement in the mixer within the tolerance specified. Provide
205 means for checking the quantity or rate of flow of asphalt cement
206 into the mixer.
207

208 (8) **Thermometric Equipment.** An armored thermometer of
209 adequate range shall be included in the bituminous feed line near
210 the charging valve at the mixer unit.
211

212 Also, the plant shall be equipped with a dial-scale,
213 mercury-actuated thermometer, or an electric pyrometer placed at
214 the discharge chute of the drier to register automatically or show
215 the temperature of the heated aggregate. The heat indicating
216 device shall be accurate to the nearest 10 degrees F. Install the
217 heat indicating device such that it will reflect a fluctuation of 10
218 degrees F on the aggregate temperature within one minute.
219

220 The Engineer may require replacement of thermometers by
221 an acceptable temperature-recording apparatus for better
222 regulation of the aggregate temperature at no cost to the State.
223

224 (9) **Dust Collector.** The plant shall be equipped with a dust
225 collector constructed to waste or return uniformly to the hot elevator
226 the material collected.
227

228 **(10) Safety Requirements.** Provide adequate and safe
229 stairways to the mixer platform and sampling points. Place
230 guarded ladders to other plant units at points where accessibility to
231 plant operations is required. Provide accessibility to the top of truck
232 bodies by a platform or other suitable device to enable the
233 Engineer to obtain sampling and mixture temperature data.
234 Provide a hoist or pulley system to raise scale calibration
235 equipment, sampling equipment and other similar equipment from
236 the ground to the mixer platform and return. Thoroughly guard and
237 protect gears, pulleys, chains, sprockets and other dangerous
238 moving parts. Provide ample and unobstructed space on the
239 mixing platform. Maintain a clear and unobstructed passage in and
240 around the truck loading area. Keep this area free of drippings
241 from the mixing platform.
242

243 **(11) Mineral Filler Feed.** Feed the filler, when used, to an
244 accuracy of 10 percent of the required weight. Thoroughly dry the
245 filler. Do not feed the filler through the drier system. Feed the filler
246 material directly into the mixer as near the center as possible for
247 batch type operation.
248

249 **(D) Requirements for Batching Plants.**
250

251 **(1) Weigh Box or Hopper.** Include a means for accurately
252 weighing each size of aggregate in a weigh box or hopper
253 suspended on scales and ample in size to hold a full batch without
254 hand raking or running over. The gate shall close tightly so that no
255 material shall leak into the mixer while weighing a batch.
256

257 **(2) Asphalt Cement Control.** The equipment used to measure
258 the asphalt cement shall be accurate to within ± 0.5 percent. The
259 asphalt cement bucket shall be a non-tilting type with a loose sheet
260 metal cover. Introduce the binder uniformly into the mixer along
261 the center of the mixer parallel to the mixer shafts, or by pressure
262 spraying. Heat the discharge valve or valves and spray bar of the
263 asphalt cement bucket adequately. Drain the steam jackets
264 efficiently, when used. The connections shall not interfere with the
265 efficient operation of the bituminous scales. The capacity of the
266 asphalt cement bucket shall be at least 15 percent greater than the
267 weight of asphalt cement required in batches. The plant shall have
268 an adequately heated, quick-acting, non-drip, charging valve
269 located directly over the asphalt cement bucket.
270

271 The indicator dial shall have a capacity of at least 15 percent
272 greater than the quantity of asphalt cement used in a batch. The
273 dial shall be in full view of the mixer operator. Discharge the

asphalt cement required for one batch in not more than 15 seconds after the flow has started. The size and spacing of the spray bar openings shall provide a uniform application of asphalt cement for the full length of the mixer. Provide the section of the bituminous line between the charging valve and the spray bar with a valve and outlet for checking the meter when a metering device is substituted for an asphalt cement bucket.

(3) **Mixer.** The batch mixer shall be capable of producing a uniform mixture within the job-mix tolerances. When not enclosed, equip the mixer box with a dust hood to prevent loss of dust. The mixer shall be leak-tight.

The clearance of blades from fixed and moving parts shall not exceed 1 inch unless the maximum diameter of the aggregate in the mix exceeds 1.25 inches, in which case the clearance shall not exceed 1.5 inches.

(4) **Control of Mixing Time.** The mixer shall have a timing device that shows by a definite audible or visual signal the expiration of the mixing period. The device shall accurately measure the time of mixing to within five seconds.

The dry mixing period is defined as the interval of time between the opening of the weigh box gate and the start of introduction of asphalt cement. The wet mixing period is the interval of time between the start of introduction of asphalt cement and the opening of the mixing gate.

(E) Requirements for Continuous Mixing Plants.

(1) **Aggregate Proportioning.** The plant shall include means for accurately proportioning each size of aggregate.

The plant shall have a feeder mounted under each compartment bin. Each compartment bin shall have an accurately controlled individual gate to form an orifice for volumetrically measuring the material drawn from each compartment. The feeding orifice shall be rectangular with one dimension adjusted by positive mechanical means provided with a lock.

Each gate shall have indicators to show the respective gate opening in inches.

318 The fine bin shall have a vibrating unit. Provide a positive
319 system to show the level of material in each bin, and as the level of
320 material in one bin approaches the strike-off capacity of the feed
321 gate, the device shall automatically close down the plant instantly.
322 The Engineer will not permit the plant to operate unless this
323 automatic system is in good working condition.
324

325 **(2) Weight Calibration of Aggregate Feed.** Calibrate gate
326 openings by weighing test samples. Make provisions so that the
327 materials fed out of individual orifices may be bypassed to
328 individual test boxes. Equip the plant to conveniently handle
329 individual test samples weighing not less than 200 pounds.
330 Provide accurate scales of adequate capacities to weigh such test
331 samples.
332

333 **(3) Synchronization of Aggregate Feed and Asphalt Cement**
334 **Feed.** Provide means to afford positive interlocking control
335 between the flow of aggregate from the bins and the flow of asphalt
336 cement from the meter or other proportioning device satisfactorily.
337 Control this by interlocking mechanical means.
338

339 The mechanically driven aggregate feeders shall be
340 connected directly with the drive on the asphalt binder pump.
341 Equip the drive shaft on the feed with a revolution counter reading
342 to 1/100 revolution and with sufficient capacity to register the total
343 number of revolutions in a day's run.
344

345 **(4) Mixer.** Include a continuous mixer of an acceptable type,
346 adequately heated and capable of producing a uniform mixture
347 within the job-mix tolerances.
348

349 The mixer shall have a discharge hopper with dump gates
350 that will permit rapid and complete discharge of the mixture. The
351 paddles shall be adjustable for angular position on the shafts and
352 reversible to retard the flow of the mix. The mixer shall have a
353 manufacturer's plate giving the net volumetric contents of the mixer
354 at the several heights inscribed on a permanent gage. Provide
355 charts showing the rate of feed of aggregate per minute for the
356 aggregate being used.
357

358 **(F) Requirements for Drier-Drum Mixing Plant.**
359

360 **(1) Cold Storage for Plants Utilizing Cold-Feed Control.**
361 Drier-drum plants equipped with cold-feed control shall separate
362 the virgin aggregate for Asphalt Concrete Mix No. II into three or
363 more sizes. Separate the virgin aggregate for Asphalt Concrete
364 Mix Nos. III, IV, V and VI into two or more sizes. Request written

acceptance from the Engineer when separating the aggregate for Asphalt Concrete Mix No. II into less than three sizes.

After separating the aggregates, store each size separately. Each of the storage, except storage for filler material, shall contribute a minimum of 10 percent to the total weight of the aggregate.

(2) Drying. Feed the aggregates directly to a drier-drum mixer at a uniform rate.

The drier-drum mixer shall have a device that shows the temperature of the material leaving the drier-drum mixer. The temperature-indicating device shall be accurate to the nearest 10 °F and show changes of 10 degrees F. in temperature of the material within one minute.

The drier-drum mixers shall have dust collectors. The dust shall be disposed of or returned to the aggregate.

(3) Proportioning for Continuous Mixing. Introduce the asphalt binder into the mixer at constant pressure through a meter. Install a gage for checking said pressure. The system shall be capable of varying the rate of delivery of binder. During production, the temperature of asphalt binder shall not vary more than 40 degrees F. Heat and insulate the meter and lines. Equip the binder storage with a device for automatic plant cut-off when the level of binder is lowered sufficiently to expose the pump suction line.

When using filler, proportion the filler by weight or volume by a method that uniformly feeds the material within 10 percent of the required amount. Discharge the filler material from the proportioning device directly into the mixer.

(4) Proportioning for Drier-Drum Mixing with Cold-Feed Control. When using cold-feed control with drier-drum mixing, equip the asphalt feeder, the aggregate feeders, the filler material feeder, and the combined aggregate feeder with devices by which the rate of feed can be determined while the plant is in full operation.

Weigh the combined aggregate using a belt scale. The belt scale shall be of such accuracy that, when the plant is operating between 30 percent and 100 percent of belt capacity, the average difference between the shown weight of material delivered and the actual weight delivered shall not exceed 1 percent of the actual weight for three 2-minute runs. For the three individual two-minute

runs, the shown weight of material delivered shall not vary from the actual weight delivered by more than 2 percent of the actual weight. Determine the actual weight of material delivered by a vehicle platform scale that has been sealed. Equip the plant so that this accuracy check can be made after each relocation and set-up, but before the first operation and at other times as required by the Engineer.

Interlock the belt scale for the combined aggregate, the proportioning devices for filler material, and the asphalt proportioning meter so that the rates of feed of the aggregates and asphalt shall be adjusted automatically to maintain the bitumen ratio (pounds of asphalt per 100 pounds of dry aggregate including filler if used) according to the approved mix design. Do not operate the plant unless this automatic system is operating.

Equip the asphalt meters and aggregate belt scales used for metering the aggregates and asphalt into the mixer with resettable totalizers, so that the actual asphalt and aggregate introduced into the mixer can be determined.

Equip the bin(s) containing the fine aggregate and filler with a vibrating unit. Before the quantity of material in one bin reaches the strike-off capacity of the feed gate, a device shall automatically close down the plant.

Determine the moisture content of the aggregate at least once during each production day. Adjust the moisture control equipment accordingly.

In the absence of an acceptable aggregate sampling device for the combined aggregate at a point before the aggregate enters the drum drier and while the plant is in full operation, provide other suitable sampling means acceptable to the Engineer.

When using filler, install a suitable, safe sampling device in each feed line or surge tank preceding the proportioning device for the filler.

(5) Drier-Drum Mixing. Mix the aggregate, filler and asphalt binder in a drier-drum mixer. Mixing shall continue for a sufficient time and at a sufficiently high temperature that, at discharge from the mixer, the sizes of aggregates are uniformly distributed through the completed mixture and particles are thoroughly and uniformly coated with asphalt binder.

459 Discharge the drier-drum mixer into a storage silo or into a
460 surge bin. Provide a means of diverting the flow of asphalt
461 concrete away from the silo or surge bin, when starting and
462 stopping the plant production, to prevent incompletely mixed
463 portions of the mixture from entering the silo.
464

465 When using a surge bin:

- 466
- 467 a. do not hold the mixture beyond one hour,
 - 468 b. do not segregate the mixture,
 - 469 c. the mixture shall not be lumpy, and
 - 470 d. the mixture shall meet temperature and quality
 - 471 requirements of the contract.
 - 472

473 The burner used for heating the aggregate in the drier-drum
474 shall achieve complete combustion of the fuel.
475

476
477
478
479 **(G) Asphalt Concrete Storage.** Store the asphalt concrete only in
480 silos. Do not stockpile the asphalt concrete. The minimum quantity of
481 asphalt concrete in storage during mixing shall be 20 tons except for the
482 period immediately following a shutdown of the plant of two hours or
483 more. Provide a means to show that the storage into each silo as
484 required is maintained.
485

486 Equip the storage silo to prevent segregation of the completed
487 mixture as the mixture is discharged into the silo.
488

489 Do not use asphalt concrete with hardened lumps in the mixture.
490 Do not use the storage facilities that contained the material with the
491 hardened lumps for further storage until the cause of the lumps is
492 corrected.
493

494 **401.05 Construction Requirements.**
495

496 **(A) Weather Limitations.** Do not place the bituminous plant mix:
497

- 498 (1) on wet surfaces, as determined by the Engineer, or
- 499 (2) when the air temperature is below 50 degrees F. or
- 500 (3) when weather conditions prevent the proper handling or
- 501 finishing of the bituminous mixtures.
- 502
- 503
- 504

505 (B) **Equipment.**

506
507 (1) **Hauling Equipment.** Trucks hauling bituminous mixtures
508 shall have tight, clean, smooth and metal beds that have been
509 thinly coated with a minimum quantity of detergent, paraffin oil, or
510 lime solution to prevent the mixture from adhering to the beds. The
511 use of diesel or petroleum-based liquids, except for paraffin oil, to
512 prevent the mixture from adhering to the beds is prohibited.

513
514 Each truck shall have a canvas cover to protect the mixture
515 from the weather. Protect each load from the weather with
516 covering securely fastened on all four sides of the truck bed.

517
518 Each truck shall raise their beds with tailgate closed before
519 discharging to prevent segregation.

520
521 Do not refuel equipment over newly paved surfaces. Refuel
522 equipment over a catch pan or a surface that will prevent the fuel
523 from coming in contact with the asphalt pavement. After the
524 refueling operation is completed, remove the above devices until
525 needed.

526
527 (2) **Bituminous Pavers.** Bituminous pavers shall be:

528
529 (a) self-contained, power-propelled units,

530
531 (b) provided with an activated screed or strike-off
532 assembly, heated if necessary, and

533
534 (c) capable of spreading and finishing courses of
535 bituminous plant mix material in lane widths applicable to the
536 specified typical section and thicknesses shown in the
537 contract.

538
539 Equip the paver with a receiving hopper having sufficient
540 capacity for uniform spreading operation. Equip the hopper with a
541 distribution system to place the mixture uniformly in front of the
542 screed.

543
544 Prior to each days paving operation, check the screed or
545 strike-off assembly surface with a straight edge to insure
546 straightness. The screed or strike-off assembly shall effectively
547 produce a finished surface of the required evenness and texture
548 without tearing, shoving or gouging the mixture. When the
549 spreading equipment leaves ridges, indentations, or other marks in
550 the surface that cannot be eliminated by rolling or prevented by

adjustment in operation, discontinue its use and furnish other acceptable equipment.

Equip the paver with an acceptable electronic screed control device. The electronic device shall include a grade sensor mounted on each side of the paver. Each sensor shall take its grade reference from a 30-foot ski for the first pass. For subsequent passes, the Contractor may substitute one ski with a joint-matching shoe riding on the finished adjacent pavement.

Demonstrate the competence of personnel operating the grade and crown control device according to the contract before placing surface courses. When the automatic control system becomes inoperative during the day's work, the Engineer will permit the Contractor to finish the day's work using manual controls. Do not resume work thereafter until the automatic control system is made operative. The Engineer may waive the use of the electronic screed control device when paving gores, shoulders, or transitions and miscellaneous reconstruction areas.

When laying mixtures, the paver shall be capable of operating at forward speeds consistent with satisfactory laying of the mixture. Do not change the forward speed of the paver after start of paving operation. If necessary, the Engineer will limit the load of the haul vehicle such that the Contractor will get satisfactory spreading.

(3) Rollers. Rollers shall be the self-propelled, steel-tired tandem pneumatic-tired or vibratory type. Rollers shall be capable of reversing without backlash. The number and weight of rollers shall be sufficient to compact the mixture to the required density while the mixture is still in a workable condition. Do not use equipment that results in excessive crushing of the aggregate. Operate the rollers according to the manufacturer's recommendations.

(a) Steel-Tired Tandem Rollers. Check the steel-wheel rims for wear. When the rolling drum is grooved or pitted, do not use the roller. Excessively worn scrapers and wetting pads shall be replaced.

Steel-tired tandem rollers used for breakdown (initial) or intermediate rolling passes shall have a minimum gross weight of 12 tons. Steel-tired tandem rollers shall provide a minimum of 250 pound weight per linear inch of width on the compaction roller (drive wheel).

597 Steel-tired tandem rollers used for finish (final) rolling
598 passes shall have a minimum gross weight of eight tons.
599

600 **(b) Pneumatic-Tired Rollers.** Pneumatic tire rollers
601 shall be the oscillating type with smooth (tread) pneumatic
602 tires of equal size and diameter. Inflate and maintain the
603 tires to the designated pressure so that the air pressure will
604 not vary more than five psi from the established pressure.
605 Space the tires so that the gaps between adjacent tires are
606 covered by the following tires.
607

608 The pneumatic-tired rollers used for breakdown or
609 intermediate rolling passes shall have a total weight that can
610 be varied to produce an operating weight per tire of not less
611 than 3,000 pounds. The tires shall have a minimum wheel
612 diameter of 20 inches. The tire inflation pressure shall be
613 within 70 psi to 75 psi when cold and 90 psi when hot.
614 During cold or windy weather condition, equip the rollers with
615 skirt-type devices (mounted around the tires) to maintain the
616 temperature of the tires during rolling operations.
617

618 The pneumatic-tired rollers used for kneading a
619 finished asphalt surface shall have a total weight that can be
620 varied to produce an operating weight per tire of not less
621 than 1,500 pounds. The tires shall have a minimum wheel
622 diameter of 15 inches and a 50 psi to 60 psi tire inflation
623 pressure.
624

625 **(c) Vibratory Rollers.** Vibratory rollers shall be
626 steel-tired tandem rollers, having a minimum weight of 7
627 tons. The vibratory rollers shall have amplitude and
628 frequency controls, speedometer, and be specifically
629 designed to compact the material on which the vibratory
630 roller is used. Operate the vibratory roller according to the
631 manufacturer's recommendations.
632

633 **(4) Hand Tools.** Keep hand tools used in the production,
634 hauling, or placement of asphalt concrete pavement clean and free
635 of contaminants. Liquids, such as diesel or mineral spirits, may be
636 used to clean the hand tools. Do not contaminate the asphalt
637 concrete pavement with cleaning liquids. Clean hand tools over a
638 catch pan with the capacity to hold all the cleaning liquid in the
639 container should it spill. Dry the hand tools before using with the
640 asphaltic material.
641

642 **(5) Material Transfer Vehicle (MTV).**
643

644 (a) **Usage.** Unless otherwise indicated in the contract
645 documents, MTV usage applies to paving projects on all
646 islands except Lanai and Molokai. When placing hot mix
647 asphalt surface course, use MTV to independently deliver
648 mixtures from hauling equipment to paving equipment. MTV
649 usage will not be required for the following:

- 650 1. Projects with less than 1,000 tons of hot mix
651 asphalt.
- 652 2. Temporary pavements.
- 653 3. Bridge deck approaches.
- 654 4. Shoulders.
- 655 5. Tapes.
- 656 6. Turning lanes.

657 (b) **Equipment.** When using MTV, install minimum
658 10 ton-capacity hopper insert in conventional paver hopper.
659 Provide the following equipment:

- 660 (1) High capacity truck unloading system in MTV
661 capable of receiving hot mix asphalt from hauling
662 equipment.
- 663 (2) MTV storage bin with minimum 15-ton
664 capacity.
- 665 (3) Auger mixing system in MTV storage bin,
666 paver hopper insert, or paver hopper to continuously
667 mix hot mix asphalt prior to discharging to conveyor
668 system.

669 (c) **Performance Evaluation.** The Engineer will
670 evaluate performance of MTV and mixing equipment by
671 measuring mat temperature profile immediately behind
672 paver screed on first day paving.

673 Six temperature profile measurements will be taken of
674 mat surface using non-contact thermometers at 50-foot
675 intervals behind paver. Each temperature profile will consist
676 of three surface temperature measurements taken
677 transversely across mat in approximately a straight line from
678 screed while paver is operating. For each profile,
679 temperature will be measured approximately 1 foot from
680
681
682
683
684
685
686
687
688
689
690
691

each edge and in middle of mat; and difference between maximum and minimum temperature measurements within each temperature profile shall not exceed 10 degrees F. If any two or more temperature profiles exceed allowable 10-degree F temperature differential, halt paving operation and adjust MTV or mixing equipment to ensure that material placed by paver meets specified temperature requirements.

Once adjustments are made, the Engineer will repeat measurement procedure to verify that material placed by paver meets specified temperature requirements. Terminate paving if temperature profile requirements are not met during repeated measurement procedure. If equipment fails to meet measurements after measurement procedure is repeated once, equipment replacement will be required before the Engineer conducts any further temperature profile measurements.

The Engineer may perform additional surface temperature profile measurements at any time during project. If two consecutive temperature profiles fail to comply with specified allowable temperature differential, halt paving operation and adjust MTV or mixing equipment to ensure that HMA placed by paver complies with temperature requirements.

(d) Transport.

1. Trailered MTV. Transport MTV by means of truck-tractor/trailer combination in accordance with Chapter 104 of Title 19, Department of Transportation, entitled 'The Movement by Permit of Oversize and overweight Vehicles on State Highways'.

2. Crossing Bridges for Self-Powered MTV. When self-powered MTV exceeds legal axle or total weight limits for vehicles under the HRS, Chapter 291, conform to the following when crossing bridges within project limits unless otherwise indicated in the contract documents:

- a. Completely remove mix from MTV.
- b. Move MTV at relatively constant speed not exceeding 5 miles per hour. MTV will not be allowed to stop on bridge.

c. No other vehicle or equipment will be allowed on bridge.

(C) Preparation of Surface. Before laying the asphalt concrete pavement, prepare the surface according to the contract. For resurfacing work, surface preparation shall include the removal of traffic tapes, and raised pavement markers, prior to application of the tack coat. The removal of thermoplastic line markings and epoxy adhesives are not required. When the prepared surface becomes damaged or unsatisfactory, repair the damaged or unsatisfactory surface at no cost to the State before work proceeds.

Paint the contact surfaces of curbs, gutters, manholes, and other structures with a thin, uniform coating of asphalt paint before placing the bituminous mixture against them.

For resurfacing work, bring irregular surfaces to uniform grade and cross section before paving the existing pavement. Fill and compact the holes, cracks and wheel ruts with Asphalt Concrete Pavement, Mix No. V, before resurfacing. Also, mark the location of existing manholes, valves, and handholes on the roadway so the location after paving can be determined. Unless otherwise noted, adjust all existing frame and cover to new finish pavement finish grade after finish pavement is completed.

(D) Spreading and Finishing. Lay, spread, and strike off the mixture upon an acceptable surface to the grade and elevation established. Use the bituminous pavers to distribute the mixture either over the entire width or over such partial width as may be practicable.

The longitudinal joint in one layer shall offset that in the layer immediately below by approximately 6 inches; however, the joint in the top layer shall be at the centerline of the pavement when the roadway comprises two lanes of width, or at lane lines when the roadway is more than two lanes in width.

The minimum temperature of the bituminous mixture as discharged to the paver shall not be less than 250 degrees F.

On areas where irregularities or unavoidable obstacles make the use of mechanical spreading and finishing equipment impracticable, spread, rake, and lute the mixture by hand tools. For such areas, dump, spread, and screed the mixture to give the required compacted thickness.

When the production of the mixture can be maintained and when practicable, use the pavers in echelon to place the wearing course in adjacent lanes.

787 When the lanes are required to be opened to public traffic, pave
788 the full travelway or total width of roadway each day. However, at the
789 discretion of the Engineer, the Contractor may construct a transition taper
790 at the longitudinal pavement drop so as not to leave a vertical face. The
791 transition taper shall be along the lane line and formed by a one foot slope
792 shoe attached on the paving machine, that would produce a wedge with a
793 maximum height of three inches down to zero inch. Remove the transition
794 taper before placing adjacent lifts.

795
796 The minimum and maximum allowable laying thickness for the
797 various types of mixture are specified in Table 401-II - Limits of
798 Bituminous Binder Content.

799
800 **(E) Compaction.** Immediately after spreading and striking off the
801 bituminous mixture and adjusting surface irregularities, thoroughly and
802 uniformly compact the mixture by rolling.

803
804 Initiate the compaction of the mixture when the mix temperature is
805 the highest at which the mixture can be compacted without excessive
806 horizontal movement. The temperature shall not be less than 220
807 degrees F.

808
809 Use pneumatic or steel-tired tandem rollers for initial or breakdown
810 rolling. Do not use pneumatic tire rollers for initial or breakdown rolling on
811 final lifts of a traveled way including auxiliary lanes.

812
813 Finish rolling using a tandem roller weighing not less than eight
814 tons. Roll at or above 175 degrees F.

815
816 Rolling shall begin at the sides and proceed longitudinally parallel
817 to the road centerline, each trip overlapping half the roller width, gradually
818 progressing to the crown of the road. When using vibratory roller, the
819 overlap shall be less than 6 inches. When paving in echelon or abutting a
820 previously placed lane, roll the longitudinal joint first followed by the
821 regular rolling procedures. On superelevated curves, the rolling shall
822 begin at the low side and progress to the high side by overlapping of
823 longitudinal trips parallel to the centerline.

824
825 Correct the displacements occurring as a result of the reversing
826 direction of a roller, or from other causes, at once by the use of rakes and
827 addition of fresh mixture when required. Roll so as not to displace the line
828 and grade of the edges of the bituminous mixture.

829
830 To prevent adhesion of the mixture to the rollers, keep the wheels
831 properly moistened with water or water mixed with very small quantities of
832 detergent. The Engineer will not permit excess liquid. Do not use diesel
833 or petroleum-based liquids on the rollers.

835 Along forms, curbs, headers, walls and other places not accessible
836 to the rollers, thoroughly compact the mixture with hot hand tampers,
837 smoothing irons or with mechanical tampers. On depressed areas, use a
838 trench roller or cleated compression strips under the roller to transmit
839 compression to the depressed areas.
840

841 When the mixture becomes loose and broken, mixed with dirt, or is
842 defective, remove, replace, and compact the mixture with fresh hot
843 mixture to conform with the surrounding area. Remove and replace areas
844 showing an excess or deficiency of asphalt cement.
845

846 Rollers shall move at a slow but uniform speed with the drive
847 wheels nearest the paver. Continue the rolling to attain the desired
848 density and until the roller marks are eliminated.
849

850 **(1) Courses Equal to or Greater Than 1.5 Inches Thick.** The
851 relative compaction requirement for pavement courses that have a
852 nominal compacted thickness equal to or greater than 1.5 inches
853 shall be not less than 92 percent nor greater than 97 percent based
854 on AASHTO T 209 modified by deletion of supplemental procedure
855 for Mixtures Containing Porous Aggregate. The type of rollers and
856 their relative position in the compaction sequence shall generally
857 be the Contractor's option.
858

859 **(2) Courses Less Than 1.5 Inches Thick.** Compaction to a
860 specified density for pavement courses that have a nominal
861 compacted thickness of less than 1.5 inches will not be required.
862

863 Initiate rolling by a non-vibratory steel-tired tandem roller.
864

865 Do intermediate rolling by a pneumatic tired roller. The
866 rolling shall continue until after compacting the entire surface by a
867 minimum of four coverage of the roller. Do additional coverage as
868 necessary to obtain thorough compaction of the mixture.
869

870 Finish the rolling using a steel-tired tandem roller. Continue
871 rolling until the entire surface has been compacted by a minimum
872 of three coverage of the roller and the roller marks have been
873 eliminated.
874

875 Do not use the vibratory roller.
876

877 **(3) Special Areas Not Designed For Vehicular Traffic.** The
878 relative compaction of areas such as bikeways not shown as part
879 of the roadway and other areas not subjected to vehicular traffic
880 shall be not less than 90 percent based on AASHTO T 209

modified by deletion of supplemental procedure for mixture containing porous aggregate. The type of rollers and their relative position in the compaction sequence shall generally be the Contractor's option. However, the Contractor shall increase the asphalt content by at least 0.5 percent above that used for asphaltic concrete pavements.

(F) Joints. Placing of the bituminous paving shall be as continuous as possible. Rollers shall not pass over the unprotected end of a freshly laid mixture. Form the transverse and longitudinal joints by cutting back on the previous run to expose the full depth of the course. Use a brush coat of asphalt paint on contact surfaces of transverse and longitudinal joints before placing additional mixture against the previously rolled material.

(G) Pavement Samples. Cut samples from the compacted pavement for testing within 48 hours of lay down. The cut pavement samples shall be 12 inches by 12 inches or 4-inch diameter cores, minimum. Take samples of the mixture for the full depth of the course at the location shown by the Engineer. Place and compact the sampled area with new materials to conform with the surrounding area.

(H) Surface Tolerances. The Engineer will test the surface using a ten- foot straightedge at selected locations. The variation of the surface from the testing edge of the straightedge between two contacts with the surface shall not exceed 3/16 inch.

The thickness of the finished pavement shall be within 0.02 foot of the planned thickness at points of the cross section.

When specified by the Engineer, correct irregularities of the pavement exceeding the above limits including removal and replacement at no cost to the State.

(I) Protection of Pavement. In multiple layer construction, the Engineer will not permit construction equipment except those directly connected with paving operations, on intermediate layers without written authorization by the Engineer. An intermediate layer is defined as layers other than the finished surface layer.

The Engineer will not permit traffic on courses of asphalt concrete until the asphalt concrete has cooled and set, except such traffic as may be necessary for construction purpose.

(J) Tack Coat. Apply tack coat to bituminous and concrete surfaces before placing the asphalt concrete pavement. The tack coat shall conform to Section 407 - Bituminous Tack Coat.

401.06 Method of Measurement. The Engineer will measure asphalt concrete pavement per square yard.

401.07 Basis of Payment. The Engineer will pay for the accepted asphalt concrete pavement at the contract unit price per square yard complete in place.

The price includes full compensation for preparing the surface; removing and disposing of all existing raised pavement markers and traffic tapes; furnishing the asphalt concrete pavement; spreading, furnishing, applying, and protecting the tack coat; compacting, and finishing the asphalt concrete pavement; sampling; protecting the pavement; and furnishing labor, material, tools, equipment, and incidentals necessary to complete the work.

The Engineer will make payment under:

Pay Item	Pay Unit
Asphalt Concrete Pavement, Mix No. _____	Square Yard

The Engineer may, in lieu of requiring removal and replacement, use the sliding scale pay factor to accept asphalt concrete pavements compacted to 90, 91, or 98 percent. The Engineer will make payment for the material in that production day at a reduced price arrived at by multiplying the contract unit price by the pay factor as shown in Table IV.

TABLE IV - SLIDING SCALE PAY FACTOR	
Percent Compaction	Percent Payment
>98	Removal
98	95
92 - 97	100
90 - 91	80
<90	Removal"

END OF SECTION