

## SECTION 712 - MISCELLANEOUS

Make the following Subsection a part of said Section:

Amend 712.57 Hot Applied Rubberized Sealant by revising the table to read as follows:

TESTS	SPECIFICATIONS
Brookfield Viscosity at 400°F. (ASTM D 3236)	75 poise maximum
Penetration, 125°F., 50g. 5 seconds (ASTM D 5)	50 maximum
Penetration, 77°F., 100g. 5 seconds (ASTM D 5)	10 - 25
Softening Point (ASTM D 36)	210°F.
Ductility, 77°F. (ASTM D 113)	15 cm minimum
Flexibility, 0°F. Crafcro Procedure	Pass
Recommended Pour Temperature	380°F.
Safe Heating Temperature	420°F.
Specific Gravity at 60°F. (material purity)	1.05 maximum"

END OF SECTION