

Appendix **I**

TABLES OF RESULTS

Table 1
Maui Baseyard
Fuel Station
Asbestos Survey Results

<i>Sample ID</i>	<i>Homogeneous Area</i>	<i>Material</i>	<i>Condition</i>	<i>Category</i>	<i>Friability</i>	<i>Asbestos Content</i>	<i>Estimated Quantity</i>
1901-F-A01	Ground	Concrete	Good	Misc	N/A	ND	500 ft ²
1901-F-A02						ND	
1901-F-A03						ND	
1901-F-A04	Ground	Asphalt	Good	Misc	N/A	ND	100 ft ²
1901-F-A05						ND	
1901-F-A06						ND	
1901-F-A07	Platform/ ground joint	Grey caulking	Good	Misc	N/A	ND	100 linear feet
1901-F-A08						ND	
1901-F-A09						ND	
1901-F-A10	Concrete joint	Black caulking	Good	Misc	N/A	ND	50 linear feet
1901-F-A11						ND	
1901-F-A12						ND	
1901-F-A13	Pipe joint on tanks	Black gasket	Good	Misc	N/A	ND	2 ft ²
1901-F-A14						ND	
1901-F-A15						ND	
1901-F-A16	Diesel fuel tank	Textured coating	Good	Misc	N/A	ND	500 ft ²
1901-F-A17						ND	
1901-F-A18						ND	

ND = None Detected

*Wollastonite/Fibrous Glass

Table 1
Maui Baseyard
Maintenance Building
Asbestos Survey Results

<i>Sample ID</i>	<i>Homogeneous Area</i>	<i>Material</i>	<i>Condition</i>	<i>Category</i>	<i>Friability</i>	<i>Asbestos Content</i>	<i>Estimated Quantity</i>
1901-M-A01	Maintenance locker room ceiling/storage walls	Drywall with joint compound	Damaged	Misc	N/A	ND*	1000 ft ²
1901-M-A02						ND*	
1901-M-A03						ND*	
1901-M-A04	Maintenance locker room wall	CMU with grout	Damaged	Misc	N/A	ND	25 ft ²
1901-M-A05						ND	
1901-M-A06						ND	
1901-M-A07	Maintenance locker room electrical panel	White caulking	Good	Misc	N/A	ND	15 linear feet
1901-M-A08						ND	
1901-M-A09						ND	
1901-M-A10	Maintenance locker room floor	Concrete	Good	Misc	N/A	ND	25 ft ²
1901-M-A11						ND	
1901-M-A12						ND	

ND = None Detected

*Wollastonite/Fibrous Glass

Table 1
Maui Baseyard
Repair Shop
Asbestos Survey Results

<i>Sample ID</i>	<i>Homogeneous Area</i>	<i>Material</i>	<i>Condition</i>	<i>Category</i>	<i>Friability</i>	<i>Asbestos Content</i>	<i>Estimated Quantity</i>
1901-R-A01	Repair shop interior walls	CMU with grout	Good	Misc	N/A	ND	25 ft ²
1901-R-A02						ND	
1901-R-A03						ND	
1901-R-A04	Repair shop interior floor and panel base	Concrete	Good	Misc	N/A	ND	25 ft ²
1901-R-A05						ND	
1901-R-A06						ND	
1901-R-A07	Repair shop exterior walls	CMU	Good	Misc	N/A	ND	25 ft ²
1901-R-A08						ND	
1901-R-A09						ND	

ND = None Detected
 *Wollastonite/Fibrous Glass

Table 1
Maui Baseyard
Truck Shed
Asbestos Survey Results

<i>Sample ID</i>	<i>Homogeneous Area</i>	<i>Material</i>	<i>Condition</i>	<i>Category</i>	<i>Friability</i>	<i>Asbestos Content</i>	<i>Estimated Quantity</i>
1901-S-A01	Truck shed floor and curbs	Concrete	Good	Misc	N/A	ND	100 ft ²
1901-S-A02						ND	
1901-S-A03						ND	

ND = None Detected

Table 2
Maui Baseyard
Fuel Station
Lead Survey Results

Sample ID	Int/Ext	Homogeneous Areas	Color	Substrate	Condition	Laboratory Reporting Limit (mg/kg)	Results (mg/kg)
1901-F-L01	Ext	Parking lines	White/yellow composite	Asphalt/concrete	Fair	40	BRL
1901-F-L02	Ext	Parking bollards	Yellow	Concrete	Fair	110	75000
1901-F-L03	Ext	Fuel tank pipes	White	metal	Fair	45	BRL
1901-F-L04	Ext	Fuel tanks	White	Concrete	Fair	40	BRL
<i>1901-F-L05</i>	<i>Ext</i>	<i>Fuel tank motor & pipes</i>	<i>Red</i>	<i>Metal</i>	<i>Fair</i>	<i>81</i>	<i>180*</i>
1901-F-L06	Ext	Pipes	Green	Metal	Fair	50	BRL
<i>1901-F-L07</i>	<i>Ext</i>	<i>Canopy pillars</i>	<i>Brown</i>	<i>Concrete</i>	<i>Fair</i>	<i>40</i>	<i>400*</i>

BRL = Below Reporting Limit

**Lead-Containing Paint*

Bold - Lead-Based Paint

Table 2
Maui Baseyard
Maintenance Building
Lead Survey Results

Sample ID	Int/Ext	Homogeneous Areas	Color	Substrate	Condition	Laboratory Reporting Limit (mg/kg)	Results (mg/kg)
1901-M-L01	Int	Locker room ceiling/walls	Off-white	Drywall	Fair	40	BRL
1901-M-L02	Int	Locker room walls	Off-white	CMU	Fair	41	BRL
<i>1901-M-L03</i>	<i>Int</i>	<i>Conduit</i>	<i>Off-white</i>	<i>Metal</i>	<i>Poor</i>	<i>42</i>	<i>95*</i>

BRL = Below Reporting Limit

**Lead-Containing Paint*

Bold = Lead-Based

Table 2
Maui Baseyard
Repair Shop
Lead Survey Results

Sample ID	Int/Ext	Homogeneous Areas	Color	Substrate	Condition	Laboratory Reporting Limit (mg/kg)	Results (mg/kg)
1901-R-L01	Int	Wall	Off-white	Concrete/C MU	Fair	40	BRL
<i>1901-R-L02</i>	<i>Int</i>	<i>Conduit</i>	<i>Off-white</i>	<i>Metal</i>	<i>Fair</i>	<i>43</i>	<i>180*</i>
<i>1901-R-L03</i>	<i>Ext</i>	<i>Junction/conduit</i>	<i>Grey</i>	<i>Metal</i>	<i>Intact</i>	<i>86</i>	<i>3800*</i>
<i>1901-R-L04</i>	<i>Ext</i>	<i>Wall</i>	<i>Brown</i>	<i>CMU</i>	<i>Fair</i>	<i>64</i>	<i>84*</i>

BRL = Below Reporting Limit

**Lead-Containing Paint*

Bold = Lead-Based

Table 2
Maui Baseyard
Truck Shed
Lead Survey Results

Sample ID	Int/Ext	Homogeneous Areas	Color	Substrate	Condition	Laboratory Reporting Limit (mg/kg)	Results (mg/kg)
1901-S-L01	Int	Wall/conduit	Grey	Metal	Fair	40	BRL

BRL = Below Reporting Limit

**Lead-Containing Paint*

Bold = Lead-Based